

# Long Oil Alkyd

Product	Oil	Oil Length	Solvent	Solid %	Acid Value (mgrKOH/gr)	Viscosity (Stoke)	Color (Gardner)	uses
Long Oil 400	Soybean Fatty Acid	57	white spirit	70%	6-10	800-1400	2	High gloss paint enamels, Varnishes
Long Oil 401	Soybean Fatty Acid	57	white spirit	70%	6-10	600-1100	3	Primers, Under coats, Architectural finishes, Industrial enamels
Long Oil 402	Soybean Fatty Acid	57	white spirit	70%	6-12	600-1300	4	Primers, Under coats, Architectural finishes, Industrial enamels
Long Oil 470	Soybean Fatty Acid	54	white spirit	70%	6-10	800-1200	2	High gloss paint enamels, Varnishes
Long Oil 471	Soybean Fatty Acid	54	white spirit	70%	6-10	600-1000	3	Primers, Under coats, Architectural finishes, Industrial enamels
Long Oil 405	Soybean Fatty Acid	54	white spirit	70%	6-12	600-1000	4	Primers, Under coats, Architectural finishes, Industrial enamels