

Short Oil Alkyd

| Product | Oil | Oil Length | Solvent | Solid % | Acid Value (mgrKOH/gr) | Viscosity (Stoke) | Color (Gardner) | uses |
|---------------|--------------------|------------|---------|---------|------------------------|-------------------|-----------------|--|
| Short Oil 600 | Soybean Fatty Acid | 30 | xylene | 60% | 6-10 | 50-100 | 2 | Quick dry, Hammer paints |
| Short Oil 601 | Soybean Fatty Acid | 36 | xylene | 60% | 6-12 | 120-250 | 3 | Stoving enamels excellent color retention, NC & Amino resins compatible |
| Short Oil 602 | Soybean Fatty Acid | 30 | xylene | 60% | 6-12 | 150-250 | 3 | Quick dry, Hammer paints |
| Short Oil 603 | Soybean Fatty Acid | 30 | xylene | 65% | 6-10 | 150-250 | 2 | Quick dry, Hammer paints |
| Short Oil 604 | Soybean Fatty Acid | 36 | xylene | 65% | 6-12 | 300-550 | 3 | Stoving enamels excellent color retention, NC & Amino resins compatible |
| Short Oil 605 | Soybean Fatty Acid | 30 | xylene | 65% | 6-12 | 150-250 | 3 | Quick dry, Hammer paints |